

## OTC Model Rule (Adhesives & Sealants) Update

**January 4, 2012** -- The following is based on information obtained on the Ozone Transport Commission (OTC) web-site ([www.otcair.org](http://www.otcair.org)) and is subject to change.

All OlyBond Insulation Adhesives including OlyBond Classic, OlyBond500 and OlyBond500 SpotShot (regular and green) have less than 11 grams of VOC per liter of adhesive and are therefore **exempt** from the OTC Model Rule for Adhesives. See Section 4, 1 [c] which exempts adhesives that contain less than 20 grams of VOC per liter of adhesive.

All OMG insulation adhesives far exceed the minimum standards set by the OTC Model Rule for Adhesives as outlined below:

“Non-membrane roof installation adhesive” as defined in Section 2, is set at 300 grams VOC per liter.

\* OlyBond Insulation Adhesives have been tested following methodology specified in EPA Method 24, modified for multi-component systems and fast curing systems. Volatile content was determined gravimetrically per ASTM D2369 on each system mixed 1:1 by volume.

### Results

- OlyBond500 & OlyBond500 SpotShot      VOC = 5 g/L
- OlyBond500 Green                              VOC = 11 g/L
- OlyBond Classic:                                VOC = 11 g/L